

EPICON B-100 PRIMER

(EP B 100)

PRODUCT DESCRIPTION

EPICON B-100 PRIMER is a two pack epoxy primer for brass surface, based on a combination of epoxy resin, curing agent and selected pigments.

It has excellent adhesion on brass surface and excellent water resistance.

PRODUCT INFORMATION

Type	Epoxy primer for brass				
Recommended Use	For propeller of ocean-going vessels				
Type of binder	Epoxy resin				
Mixing Ratio	Base : Hardener = 79 : 21 (by volume)				
Color	Yellow				
Flash Point	Base : 19.5℃, Hardener : 19.3 ℃				
Solids by Volume	46% ± 2 (Test Method : ISO-3233)				
VOC	406 g/l (EPA Method 24), 465 g/l (Korea Clean Air Conservation Act)				
Coverage(Theoretical)	6.58 m ² /l [0.152 l/m ²] at D.F.T 70μm				
Wet Film Thickness	152 μm				
Dry Film Thickness	70 μm				
Drying Time (at D.F.T. 70μm)	Temperature	5℃	10℃	20℃	30℃
	Surface Dry	1.5 Hrs.	60 min.	30 min.	20 min.
	Hard Dry	8 hrs.	6 hrs.	3 hrs.	2 hrs.
Painting Interval (at D.F.T. 70μm)	Minimum	8 hrs.	6 hrs.	3 hrs.	2 hrs.
	Maximum	7 days	7 days	5 days	3 days
Pot Life	70 min.		60 min.	45 min.	30 min.
Thinner	EPICON THINNER, EPOXY THINNER A				
Method of Application	Airless spray, Brush, Roller				
Condition of Application	Temperature	: Minimum		0℃	
	Humidity	: Maximum		85 % R. H.	
	For Airless spray ;				
	Tip No.	: GRACO 519 - 621			
	Paint output pressure	: 6.9 – 10.3 MPa			
	Viscosity	: 60 - 120 sec.(Ford Cup No.4)			
Preferable Preceding Coats	-				
Preferable Subsequent Coats	CMP BIOCLEAR SG-R				
Packaging	Two pack product				

TECHNICAL DATA (at 70 μ m)

Temp (°C)		-5	0	5	10	15	20	25	30	35	40
Item											
Set to touch		-	2H	1.5H	60m	45m	30m	25m	20m	-	-
Dry to recoat	Min.	-	12H	8H	6H	4.5H	3H	2.5H	2H	-	-
	Max.	-	7D	7D	7D	7D	5D	5D	3D	-	-
Dry to hard		-	12H	8H	6H	4.5H	3H	2.5H	2H	-	-
Dry to immerse	Body	-	-	-	-	-	-	-	-	-	-
	Touch-up	-	-	-	-	-	-	-	-	-	-
Dry to Touch-up		-	12H	8H	6H	4.5H	3H	2.5H	2H	-	-
Pot life		-	70m	70m	60m	50m	45m	35m	30m	-	-
Shelf life (M)		-	12M	12M	12M	12M	12M	12M	12M	-	-
Max. heat resistance		-									

Abbreviation ; Y : Year, M : Month, D : Day, H : Hour, m : Minute

Notes :

1. Since it has short pot life, please mix just required and use it immediately.
2. In common with all epoxy coatings, EPICON B-100 PRIMER will show chalking and fading on exposure to UV light.

RECOMMENDABLE SURFACE PREPARATION

All surfaces to be free from various contaminants (oil, grease, dust, spray dust and etc.) and keep surfaces dry.
Kindly consult CSP sales office for specific information.

SAFETY PRECAUTIONS

In order to ensure safe use of our product, please be sure to follow the safety precautions indicated on the SDS and the paint container. If you need further explanation, do not hesitate to consult our personnel or our local distributors before buying, opening, using, or disposing the product. Since product contains flammable materials, keep away from sparks and open flame. No smoking should be permitted in the area on painting.

Wear an appropriate protector (eye and face protection, protective clothing, barrier creams, etc) when mixing, applying, or drying the paint. If products come into contact with the skin, wash thoroughly with warm water and soap or suitable cleaner. If the eyes is contaminated, irrigate with water and seek medical advice immediately.

DISCLAIMER

The information, including data, specifications, directions and recommendations, contained in this Data Sheet describes the experiment results under controlled or specially defined conditions and we do not guarantee that the Products, when used under the actual conditions of any intended use, will produce the same results. The performance of the Products in their actual use is affected by various factors, and the User must judge whether the Products are suitable for specific uses. We do not guarantee the performance of the Products under any specific operation environment other than the performance of the Products under the conditions described in this Data Sheet.

The content of this Data Sheet, which is intended for facilitation of the User's understanding and convenience of use of the Products, is subject to change at any time without prior notice. We use our best efforts to reflect the latest and most accurate information in this Data Sheet, but we will not bear any liability whatsoever relating thereto. The User must confirm that the Data Sheet is the latest version prior to using the Products.

We do not guarantee the performance or safety of the Products when used for a purpose or use other than what is described herein. Nor will we be liable for any explanation or guarantee provided by any distributor or sales agent with respect to the Products, other than what is described in this Data Sheet.

Furthermore, each of the Products described herein is composed of various chemical substances, some of which may contain toxic and/or harmful ingredients and may cause harmful results as a result of misuse or overuse of the Products. For specific causes of risk, conditions of use, harmfulness, etc. of each of the Products, please carefully read, prior to use of the Products, the MSDS (Material Safety Data Sheet) inserted in each of the Products. We will not be liable for any accident that may be caused in violation thereof.