

GALVANITE No.200 PRIMER

(GNT 200P)

PRODUCT DESCRIPTION

GALVANITE No.200 PRIMER is a primer for galvanized steel surface based on a combination of epoxy resin and polyamide resin pigmented with special rust-preventing pigment.

It has the following advantages;

1. Excellent adhesion to galvanized surface
2. Excellent water resistance
3. Quick dry
4. Excellent compatibility with various type of subsequent coats

PRODUCT INFORMATION

Type	Epoxy primer				
Recommended Use	As a primer on galvanized steel				
Type of binder	Epoxy				
Mixing Ratio	Base : Hardener = 84 : 16 (by volume)				
Color	White				
Flash Point	Base : 17.5 °C, Hardener : 19.5 °C				
Solids by Volume	47% ± 2 (Test Method : ISO-3233)				
VOC	530 g/l (EPA Method24), 558 g/l (Korea Clean Air Conservation Act)				
Coverage(Theoretical)	11.75 m ² /ℓ [0.085 ℓ/m ²] at D.F.T 40μm				
Wet Film Thickness	64 – 106 μm				
Dry Film Thickness	30 – 50 μm				
Drying Time (at D.F.T. 40μm)	Temperature	5 °C	10 °C	20 °C	30 °C
	Surface Dry	30 min.	20 min.	10 min.	5 min.
	Hard Dry	8 hrs.	6 hrs.	4 hrs.	3 hrs.
Painting Interval (at D.F.T. 40μm)	Minimum	18 hrs.	10 hrs.	4 hrs.	3 hrs.
	Maximum	90 days	60 days	30 days	30 days
Pot Life		36 hrs.	30 hrs.	24 hrs.	12 hrs.
Thinner	EPICON THINNER, EPOXY THINNER G				
Method of Application	Airless spray, Brush				
Condition of Application	Temperature	: Minimum - 5 °C			
	Humidity	: Maximum 85 % R.H.			
	For Airless spray ;				
	Tip No.	: GRACO 619, 719			
	Paint output pressure	: 10.8 - 13.7 MPa			
Preferable Preceding Coats	Viscosity	: 55 - 65 sec.(Ford Cup No. 4)			
	-				
Preferable Subsequent Coats	Various paint (except for inorganic type paint and polyurethane type paint)				
Packaging	Two pack product				

TECHNICAL DATA (at 40 μ m)

Temp (°C)		-5	0	5	10	15	20	25	30	35	40
Item											
Set to touch		60m	40m	30m	20m	15m	10m	7.5m	5m	4m	3m
Dry to recoat	Min.	40H	28H	18H	10H	7H	4H	3.5H	3H	2.5H	2H
	Max.	90D	90D	90D	60D	30D	30D	30D	30D	30D	30D
Dry to hard		14H	10H	8H	6H	5H	4H	3.5H	3H	2.5H	2H
Dry to immerse	Body	-	-	-	-	-	-	-	-	-	-
	Touch-up	-	-	-	-	-	-	-	-	-	-
Dry to Touch-up		40H	28H	18H	10H	7H	4H	3.5H	3H	2.5H	2H
Pot life		50H	44H	36H	30H	27H	24H	18H	12H	10H	8H
Shelf life (M)		12M	12M	12M	12M	12M	12M	12M	12M	12M	12M
Max. heat resistance (Dry)		150°C (Non-continuous)									

Abbreviation ; Y : Year, M : Month, D : Day, H : Hour, m : Minute

Notes :

- BANNOH series is considered as undercoat for polyurethane coating.
Kindly consult CSP sales office.
- When temperature is at low temperature, curing/drying time will be longer.
(Preferable curing/drying temperature : above 5°C).
- In common with all epoxy coatings, GALVANITE No.200 PRIMER will show chalking and fading on exposure to UV.

RECOMMENDABLE SURFACE PREPARATION

All surfaces to be free from various contaminants (oil, grease, dust, spray dust and etc.) and keep surfaces dry.
Kindly consult CSP sales office for specific information.

SAFETY PRECAUTIONS

In order to ensure safe use of our product, please be sure to follow the safety precautions indicated on the SDS and the paint container. If you need further explanation, do not hesitate to consult our personnel or our local distributors before buying, opening, using, or disposing the product. Since product contains flammable materials, keep away from sparks and open flame. No smoking should be permitted in the area on painting.

Wear an appropriate protector (eye and face protection, protective clothing, barrier creams, etc) when mixing, applying, or drying the paint. If products come into contact with the skin, wash thoroughly with warm water and soap or suitable cleaner. If the eyes is contaminated, irrigate with water and seek medical advice immediately.

DISCLAIMER

The information, including data, specifications, directions and recommendations, contained in this Data Sheet describes the experiment results under controlled or specially defined conditions and we do not guarantee that the Products, when used under the actual conditions of any intended use, will produce the same results. The performance of the Products in their actual use is affected by various factors, and the User must judge whether the Products are suitable for specific uses. We do not guarantee the performance of the Products under any specific operation environment other than the performance of the Products under the conditions described in this Data Sheet.

The content of this Data Sheet, which is intended for facilitation of the User's understanding and convenience of use of the Products, is subject to change at any time without prior notice. We use our best efforts to reflect the latest and most accurate information in this Data Sheet, but we will not bear any liability whatsoever relating thereto. The User must confirm that the Data Sheet is the latest version prior to using the Products.

We do not guarantee the performance or safety of the Products when used for a purpose or use other than what is described herein. Nor will we be liable for any explanation or guarantee provided by any distributor or sales agent with respect to the Products, other than what is described in this Data Sheet.

Furthermore, each of the Products described herein is composed of various chemical substances, some of which may contain toxic and/or harmful ingredients and may cause harmful results as a result of misuse or overuse of the Products. For specific causes of risk, conditions of use, harmfulness, etc. of each of the Products, please carefully read, prior to use of the Products, the MSDS (Material Safety Data Sheet) inserted in each of the Products. We will not be liable for any accident that may be caused in violation thereof.

The information given in this sheet is effective at the date shown above and subject to revision from time to time without notice.