

# SEAFLO NEO CF Z

(SFL N CF Z)

## PRODUCT DESCRIPTION

**SEAFLO NEO CF Z** a high performance antifouling incorporating a new biocide technology with a synthetic agent combined with zinc acrylate polymer. This antifouling has been designed as a premium solution for vessels trading at a wide range of speed and activity, where the main focuses are long term hull performance, reducing hull resistance and fuel saving by maintaining an optimum leached layer.

## PRODUCT INFORMATION

REDUCED INFORMATION					
Type	Ultra low friction, low FIR, TBT free, cuprous oxide free hydrolysis antifouling				
Recommended Use	Antifouling paint for the underwater hulls of high-activity vessels such as container ships and VLCCs operating in tropical trades.				
Type of binder	Zinc acrylate polymer				
Color	Red, Light Red				
Flash Point	24.5 °C				
Solids by Volume	50% ± 2 (Test Method : ISO-3233)				
VOC	403 g/l(EPA Method24), 446 g/l(Korean Clean Air Conservation Act)				
Coverage(Theoretical)	5.00 m <sup>2</sup> /ℓ [0.200 ℓ/m <sup>2</sup> ] at D.F.T 100μm				
Wet Film Thickness	150 – 330 μm				
Dry Film Thickness	75 – 165 μm				
Drying Time (at D.F.T. 100μm)	Temperature	5℃	10℃	20℃	30℃
	Surface Dry	3 hrs.	2 hrs.	1 hr.	30 min.
	Hard Dry	12 hrs.	8 hrs.	5 hrs.	4 hrs.
Painting Interval (at D.F.T. 100μm)	Minimum	12 hrs.	8 hrs.	5 hrs.	4 hrs.
	Maximum	-	-	-	-
Dry to Launch (at D.F.T. 100μm)	Minimum	18 hrs.	12 hrs.	10 hrs.	9 hrs.
	Maximum	-	-	-	-
Thinner	RAVAX THINNER, CR/ACRI THINNER A				
Method of Application	Airless spray, Brush, Roller				
Condition of Application	Temperature	: Minimum - 5 °C			
	Humidity	: Maximum 85 % R.H.			
	For Airless spray ;				
	Tip No.	: GRACO 619 ~ 723			
	Paint output pressure	: 11.7 – 14.7 MPa			
	Viscosity	: 1.5 - 2.5 Pa·s			
Preferable Preceding Coats	BANNOH 1500 R Z, SILVAX SQ-K, CMP AC-10, etc.				
Preferable Subsequent Coats	-				
Packaging	One pack product				

**TECHNICAL DATA (at 100 $\mu$ m)**

Temp (°C)		-5	0	5	10	15	20	25	30	35	40
Item											
<b>Set to touch</b>		6H	4H	3H	2H	1.5H	1H	1H	30m	30m	30m
<b>Dry to recoat</b>	<b>Min.</b>	22H	16H	12H	8H	6H	5H	4.5H	4H	3H	3H
	<b>Max.</b>	-	-	-	-	-	-	-	-	-	-
<b>Dry to hard</b>		22H	16H	12H	8H	6H	5H	4.5H	4H	3H	3H
<b>Dry to immerse*)</b>	<b>Body</b>	42H	30H	18H	12H	11H	10H	9H	9H	8.5H	8H
	<b>Touch-up</b>	36H	24H	14H	12H	10H	8H	8H	7.5H	7H	6H
<b>Dry to Touch-up</b>		22H	16H	12H	8H	6H	5H	4H	4H	3H	3H
<b>Pot life</b>		-	-	-	-	-	-	-	-	-	-
<b>Self life (M)</b>		12M	12M	12M	12M	12M	12M	12M	12M	12M	12M
<b>Max. heat resistance</b>		60°C (Non-continuous)									

Abbreviation ; Y : Year, M : Month, D : Day, H : Hour, m : Minute

**Notes :**

- \*) If applied anti-fouling coat is higher than above the recommended DFT or number of coat is two or more, the dry time to be immersed is necessary to be longer for physical resistance, flooding and sailing.
- For the expectations of performance for this product in static conditions, it is necessary to consider location conditions such as fouling activity, water temperatures, and pollution level. For more information please consult a CMP office or representative.
- Slight color variation such as whitening can be expected after immersion and climatic exposure, although this phenomenon does not affect the anti-fouling performance.

**RECOMMENDABLE SURFACE PREPARATION**

All surfaces to be free from various contaminants (oil, grease, dust, spray dust and etc.) and keep surfaces dry. Kindly consult CSP sales office for specific information.

**SAFETY PRECAUTIONS**

In order to ensure safe use of our product, please be sure to follow the safety precautions indicated on the SDS and the paint container. If you need further explanation, do not hesitate to consult our personnel or our local distributors before buying, opening, using, or disposing the product. Since product contains flammable materials, keep away from sparks and open flame. No smoking should be permitted in the area on painting.

Wear an appropriate protector (eye and face protection, protective clothing, barrier creams, etc) when mixing, applying, or drying the paint. If products come into contact with the skin, wash thoroughly with warm water and soap or suitable cleaner. If the eyes is contaminated, irrigate with water and seek medical advice immediately.

**DISCLAIMER**

The information, including data, specifications, directions and recommendations, contained in this Data Sheet describes the experiment results under controlled or specially defined conditions and we do not guarantee that the Products, when used under the actual conditions of any intended use, will produce the same results. The performance of the Products in their actual use is affected by various factors, and the User must judge whether the Products are suitable for specific uses. We do not guarantee the performance of the Products under any specific operation environment other than the performance of the Products under the conditions described in this Data Sheet.

The content of this Data Sheet, which is intended for facilitation of the User's understanding and convenience of use of the Products, is subject to change at any time without prior notice. We use our best efforts to reflect the latest and most accurate information in this Data Sheet, but we will not bear any liability whatsoever relating thereto. The User must confirm that the Data Sheet is the latest version prior to using the Products.

We do not guarantee the performance or safety of the Products when used for a purpose or use other than what is described herein. Nor will we be liable for any explanation or guarantee provided by any distributor or sales agent with respect to the Products, other than what is described in this Data Sheet.

Furthermore, each of the Products described herein is composed of various chemical substances, some of which may contain toxic and/or harmful ingredients and may cause harmful results as a result of misuse or overuse of the Products. For specific causes of risk, conditions of use, harmfulness, etc. of each of the Products, please carefully read, prior to use of the Products, the MSDS (Material Safety Data Sheet) inserted in each of the Products. We will not be liable for any accident that may be caused in violation thereof.

The information given in this sheet is effective at the date shown above and subject to revision from time to time without notice.